

ExxonMobil LLDPE LL 1002YB Cast Linear Low Density Polyethylene Resin

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE

Material Notes:

Product Description: LL 1002YB is an LLDPE resin designed for cast films. It offers high gloss and excellent drawdown in both blown and cast film applications. LL 1002YB may also be used as a blend partner with LDPE resins to improve film properties and processability.

Availability: Africa & Middle East, Asia Pacific, Europe, Latin America, North America and South America Additive: Antiblock: NoSlip: No

Processing Aid: No**Thermal Stabilizer:** Yes**Applications:** Cast FilmCast Stretch FilmGarment FilmGeneral PackagingHygiene filmPackaging

FilmsPersonal CareInformation provided by ExxonMobil

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-LLDPE-LL-1002YB-Cast-Linear-Low-Density-Polyethylene-Resin.php

Physical Properties	Metric	English	Comments
Density	0.918 g/cc	0.0332 lb/in ³	ExxonMobil method
Melt Flow	2.0 g/10 min @Load 2.16 kg, Temperature 190 °C	2.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	7.58 MPa	1100 psi	ASTM D882
Film Tensile Strength at Yield, TD	6.48 MPa	940 psi	ASTM D882
Film Elongation at Break, MD	420 %	420 %	ASTM D882
Film Elongation at Break, TD	830 %	830 %	ASTM D882
Puncture Energy	2.37 J	1.75 ft-lb	ExxonMobil Method
Elmendorf Tear Strength MD	20 g	20 g	ASTM D1922
Elmendorf Tear Strength TD	430 g	430 g	ASTM D1922
Dart Drop Test	<= 50.0 g	<= 0.110 lb	ASTM D1709A
Film Tensile Strength at Break, MD	62.1 MPa	9000 psi	ASTM D882
Film Tensile Strength at Break, TD	24.8 MPa	3600 psi	ASTM D882
1% Secant Modulus, MD	117 MPa	17000 psi	ASTM D882
1% Secant Modulus, TD	131 MPa	19000 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Melting Point	<= 248 °C	<= 478 °F	Peak Melting Point; ExxonMobil

Thermal Properties	Metric	English	method Comments
Optical Properties	Metric	English	Comments
Haze	1.7 %	1.7 %	ASTM D1003
Gloss	98 %	98 %	45°; ASTM D2457

Descriptive Properties	Value	Comments
Puncture Force	8 lbf	ExxonMobil Method

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China