

ExxonMobil LLDPE LL 6100.17 Linear Low Density Polyethylene Resin

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE

Material Notes:

Product Description: LL 6100 is a narrow molecular weight butane copolymer designed for applications that require easy processability.

This resin offers outstanding toughness and tear resistance in freezer applications for food packaging. Availability: Latin America, North

America and South America Applications: Closures and Dispensers Housewares Protective Caps Information provided by ExxonMobil

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-LLDPE-LL-610017-Linear-Low-Density-Polyethylene-Resin.php

Physical Properties	Metric	English	Comments
Density	0.925 g/cc	0.0334 lb/in ³	ExxonMobil method
ESCR 10% Igepal®	330 hour	330 hour	F50; ASTM D1693B
Melt Flow	20 g/10 min @Load 2.16 kg, Temperature 190 °C	20 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	11.7 MPa	1700 psi	ASTM D638
Elongation at Break	350 %	350 %	ASTM D638
Flexural Modulus	0.427 GPa	62.0 ksi	2% Secant; ASTM D638
Flexural Modulus, 1% Secant	483 MPa	70000 psi	ASTM D638

Thermal Properties	Metric	English	Comments
Melting Point	<= 255 °C	<= 491 °F	Peak Melting Point; ExxonMobil method

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China