

ExxonMobil Mobilarma 777

Category : Fluid , Lubricant

Material Notes:

The Mobilarma 700 Series contains three premium performance rust preventives that cover a range of applications including storage and inter-operational activities. The Mobilarma 777 and 778 are intended for protection cold-rolled sheet and coiled steel in the metal industry. Mobilarma 798 is intended for the lubrication and rust protection of wire rope in industrial, construction, mining and marine applications. The Mobilarma 700 Series products exhibit excellent water displacing properties and form thin tenacious films that protect surfaces even under severe conditions that include high moisture levels and exposure to acid or corrosive fumes. The Mobilarma 777 and 778 form wet, oily and extremely thin barrier films that are not tacky so that they will not attract dirt or other foreign matter. They will protect sheet and coiled steel for up to twelve months, even under severe conditions that include variations in humidity and exposure to acid fumes that might be found in the vicinity of pickling operations. Mobilarma 798 forms a grease-like film that protects wire ropes from corrosion tendencies of salt spray and moisture- laden atmospheres. It is effective throughout the extremes of temperature that may be encountered at sea and gives good protection against mild acids. It is pliable at -35oC and will not drip at 60oC. It resists throw-off in high-speed service and adheres without being tacky or stringy. The film is self-healing and does not chip. Mobilarma 777 and 778 are recommended for use as: Protective coatings for cold-rolled sheet and coiled steel; Coatings for precision machined parts and instruments for storage; A die lubricant (Mobilarma 778) in some light duty pressing operation

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Mobilarma-777.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.860 g/cc	0.860 g/cc	ASTM D1298
Kinematic Viscosity at 40°C (104°F)	13 cSt	13 cSt	ASTM D445

Thermal Properties	Metric	English	Comments
Pour Point	-6.00 °C	21.2 °F	ASTM D97
Flash Point	120 °C	248 °F	ASTM D92

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China