

ExxonMobil Mytex™ AN17K-01

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

Material Notes:

Rubber modified polypropylene for automotive interior applications. Information provided by ExxonMobil Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Mytex-AN17K-01.php

Physical Properties	Metric	English	Comments
Density	0.890 g/cc	0.0322 lb/in ³	
Melt Flow	22 g/10 min @Load 2.16 kg, Temperature 230 °C	22 g/10 min @Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	58	58	15s; LAB034
Tensile Strength, Yield	>= 15.00 MPa	>= 2176 psi	2 in/min; LAB032
Flexural Modulus	>= 0.5000 GPa	>= 72.52 ksi	1% tangent, 0.05 in/min.; LAB033
Izod Impact, Notched	>= 5.50 J/cm	>= 10.3 ft-lb/in	LAB034

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	60.0 °C	140 °F	LAB036

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China