

ExxonMobil Mytex™ AS23K(W)-01

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Talc filled compounded polypropylene produced for automotive interior applications Information provided by ExxonMobil Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Mytex-AS23KW-01.php

Physical Properties	Metric	English	Comments
Density	0.990 g/cc	0.0358 lb/in ³	
Melt Flow	18 g/10 min @Load 2.16 kg, Temperature 230 °C	18 g/10 min @Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	95	95	
Tensile Strength, Yield	26.00 MPa	3771 psi	2 in/min; LAB032
Flexural Modulus	1.900 GPa	275.6 ksi	1% tangent, 0.05 in/min.; LAB033
Izod Impact, Notched	0.598 J/cm	1.12 ft-lb/in	LAB034

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	112 °C	234 °F	LAB036

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China