

ExxonMobil Oppalyte™ 42MH647 OPP Film

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Film Grade

Material Notes:

Product Description: A super white opaque, modified higher density, biaxially oriented polypropylene film, acrylic coated two sides. It provides outstanding performance on all packaging machines. **Availability:** Africa & Middle East, Asia Pacific and Europe **Key Features:** Low sealing threshold High seal strengths even under low pressure sealing Good aroma barrier Excellent packaging machine performance Outstanding opacity, white background and reduced show-through Excellent stiffness Ideal support for normal ink systems Water based coatings **Features:** Acrylic Coated Flavor & Aroma Barrier Light Barrier **Applications:** Bakery Biscuits/Cookie/Crackers Box Overwrap Confectionery, Chocolate Confectionery, Gum Confectionery, Sugar Crisps and Snacks Dry Foods and Beverage Powders Health and Beauty Care Household and Detergents Pet food **Uses:** Box Overwrap Flexible Packaging HFFS Flexible Packaging Pre-made Bags – Flexible Packaging VFFS Flexible Packaging **Processing Method:** Cold Seal Adhesive, Solvent Flexographic Printing, Solvent Rotogravure Printing and Surface Print **Unsupported Information provided by ExxonMobil**

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Oppalyte-42MH647-OPP-Film.php

Physical Properties	Metric	English	Comments
Water Vapor Transmission	0.807 g/m ² /day	0.0520 g/100 in ² /day	85% RH; ExxonMobil Method
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	4.04 g/m ² /day	0.260 g/100 in ² /day	90% RH; ExxonMobil Method
	@Temperature 38.0 °C	@Temperature 100 °F	
Oxygen Transmission Rate	745 cc/m ² /day	48.0 cc/100 in ² /day	0% RH; ExxonMobil Method
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	751 cc/m ² /day	48.4 cc/100 in ² /day	Wet, 75% RH; ExxonMobil Method
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Thickness	43.2 microns	1.70 mil	ExxonMobil Method
Coating Weight	30.6 g/m ²	19.1 lb/ream	ExxonMobil Method

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	170 %	170 %	7.9 in/min, 4.9 in Jaw Separation; ExxonMobil Method
Film Elongation at Break, TD	55 %	55 %	7.9 in/min, 4.9 in Jaw Separation; ExxonMobil Method
Modulus of Elasticity	1.70 GPa	247 ksi	MD; ExxonMobil Method
	2.80 GPa	406 ksi	TD; ExxonMobil Method
Coefficient of Friction	0.25	0.25	Both Sides; ExxonMobil Method

Mechanical Properties	Metric ^{#5 mm}	English ^{#1}	Comments
Seal Strength	@Pressure 0.276 MPa, Temperature 130 °C	@Pressure 40.0 psi, Temperature 266 °F	Otto Bragger, 0.5 sec, ExxonMobil Method
Film Tensile Strength at Break, MD	105 MPa	15200 psi	7.9 in/min, 4.9 in Jaw Separation; ExxonMobil Method
Film Tensile Strength at Break, TD	185 MPa	26800 psi	7.9 in/min, 4.9 in Jaw Separation; ExxonMobil Method

Thermal Properties	Metric	English	Comments
Shrinkage, MD	5.0 % @Temperature 135 °C, Time 432 sec	5.0 % @Temperature 275 °F, Time 0.120 hour	ExxonMobil Method
Shrinkage, TD	3.0 % @Temperature 135 °C, Time 432 sec	3.0 % @Temperature 275 °F, Time 0.120 hour	ExxonMobil Method

Optical Properties	Metric	English	Comments
Gloss	70 %	70 %	45°; ExxonMobil Method
Transmission, Visible	25 %	25 %	ExxonMobil Method

Descriptive Properties	Value	Comments
Whiteness Index	70	
Yield	22600 in ² /lb	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China