

ExxonMobil POLYBILT™ PB 152 Bitumen Modifier Resin (discontinued **)

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate

Material Notes:

Polybilt PB 152 is an 18% VA copolymer that yields modified bitumen blends with good storage stability, increased softening point, increased high temperature viscosity and decreased penetration. PB 152 can be blended using conventional equipment, Blending time will depend on the shear rate of the equipment used and temperature. The recommended temperature range is 330 to 350°F. Information provided by ExxonMobil Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-POLYBILT-PB-152-Bitumen-Modifier-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.941 g/cc	0.0340 lb/in ³	ExxonMobil Method
Vinyl Acetate Content	19.3 %	19.3 %	ExxonMobil Method
Melt Flow	2.5 g/10 min	2.5 g/10 min	ASTM D1238

Thermal Properties	Metric	English	Comments
Melting Point	85.6 °C	186 °F	Peak Melting Temperature; ExxonMobil Method
Vicat Softening Point	61.7 °C	143 °F	ASTM D1525

Descriptive Properties	Value	Comments
Features	Thermal Stabilizer	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China