

ExxonMobil PP7035E4 Impact Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

Material Notes:

Product Description: A medium impact copolymer resin designed for injection molding applications requiring high melt flow rate.
Availability: North America
Features: Good Colorability Good Dimensional Stability Good Flow Low Temperature Impact Resistance
Uses: Bottles Consumer Applications Furniture Packaging Rigid Packaging
Processing Method: Injection Molding
 Information provided by ExxonMobil Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-PP7035E4-Impact-Copolymer.php

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in ³	ASTM D792
Melt Flow	35 g/10 min @Load 2.16 kg, Temperature 230 °C	35 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	22.8 MPa	3310 psi	2 in/min; ASTM D638
Elongation at Yield	7.6 %	7.6 %	2 in/min; ASTM D638
Flexural Modulus	1.01 GPa	146 ksi	1% secant, 0.05 in/min.; ASTM D790
	1.16 GPa	168 ksi	1% secant, 0.5 in/min; ASTM D790B
Izod Impact, Notched	1.55 J/cm	2.90 ft-lb/in	ASTM D256
Gardner Impact	21.0 J @Thickness 3.17 mm, Temperature -30.0 °C	15.5 ft-lb @Thickness 0.125 in, Temperature -22.0 °F	ASTM D5420

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	84.0 °C	183 °F	ASTM D648

Processing Properties	Metric	English	Comments
Processing Temperature	204 - 232 °C	399 - 450 °F	Typical

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China