

ExxonMobil Paxon™ BA50-100 Blow Molding Resin

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Blow Molding Grade

Material Notes:

Product Description: BA50-100 is a high molecular weight, high density polyethylene copolymer. This resin has superior stress crack resistance, high impact strength and good rigidity.
Availability: Latin America, North America and South America
Additive: Thermal Stabilizer: Yes
Antistatic: No
Applications: Agriculture Products Containers Automotive Fittings Automotive Fuel Tanks Drums Food packaging Heavy Gauge Sheet Large Part Blow Molding Pallets Portable Fuel Tanks Small Engine Fuel Tanks Thermoformed Parts
 Information provided by ExxonMobil Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Paxon-BA50-100-Blow-Molding-Resin.php

Physical Properties	Metric	English	Comments
Density	0.949 g/cc	0.0343 lb/in ³	ASTM D4883
ESCR 100% Igepal®	>= 800 hour	>= 800 hour	ASTM D1693 Condition B
Melt Flow	10 g/10 min	10 g/10 min	190 / 21.6 (HLMI); ASTM D1238
	<= 0.10 g/10 min	<= 0.10 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	26.2 MPa	3800 psi	ASTM D638
Elongation at Break	1000 %	1000 %	ASTM D638
Flexural Modulus	1.24 GPa	180 ksi	Method 1, Procedure A (1"x3"x0.125"), Tangent calculation; ASTM D790
Tensile Impact Strength	252 kJ/m ²	120 ft-lb/in ²	ASTM D1822

Thermal Properties	Metric	English	Comments
Vicat Softening Point	121 °C	250 °F	ASTM D1525
Brittleness Temperature	<= -76.1 °C	<= -105 °F	ASTM D746

Processing Properties	Metric	English	Comments
Melt Temperature	204 °C	400 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China