

ExxonMobil Santoprene® 121-60M200 Thermoplastic Vulcanizate - UV Resistant

Category: Polymer, Thermoplastic, Elastomer, TPE, Thermoplastic Vulcanizate Elastomer (TPV)

Material Notes:

Product Description: A soft, black thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material is specially formulated with high flow properties and excellent aesthetics for use in injection molded parts such as automotive glass encapsulation. This grade of Santoprene TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding. It is polyolefin based and completely recyclable. Key Features: Designed for fast, easy injection molding, especially for complex part geometries. Designed to be injected at lower molding temperatures or at lower injection pressures. Designed with higher gloss to allow for a wider range of gloss tailoring via mold surface. Designed for parts requiring good aesthetics with minimal to no flow defects or tiger stripes. EU and China RoHS compliant. Processing Method: Injection Molding and Multi Injection Molding Availability: Africa & Middle East, Europe, North America, Asia Pacific, Latin America and South Americaln formation provided by ExxonMobil Chemical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Santoprene-121-60M200-Thermoplastic-Vulcanizate-UV-Resistant.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.950 g/cc	0.950 g/cc	ASTM D792 and ISO 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	61	61	2 mm; ISO 868
Tensile Strength at Break	3.90 MPa	566 psi	Across Flow; ASTM D412 and ISO 37
Tensile Stress	2.00 MPa	290 psi	Across Flow; ASTM D412 and ISO 37
	@Strain 100 %	@Strain 100 %	
Elongation at Break	360 %	360 %	Across Flow; ASTM D412 and ISO 37

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China