

ExxonMobil Santoprene® 121-68W228 Thermoplastic Elastomer (discontinued **)

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Vulcanizate Elastomer (TPV)

Material Notes:

A soft, black thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material is specially formulated for low density foamed profile extrusion applications and has long term sealability, low temperature flexibility and heat weldability. This grade of Santoprene TPV is shear-dependent and can be processed on conventional thermoplastics equipment for extrusion. It is polyolefin based and completely recyclable. Recommended for applications requiring excellent flex fatigue resistance. Recommended for applications requiring excellent ozone resistance. Information provided by Advanced Elastomer Systems

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Santoprene-121-68W228-Thermoplastic-Elastomer-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.960 g/cc	0.960 g/cc	23°C; ASTM D792

Processing Properties	Metric	English	Comments
Processing Temperature	175 - 230 °C	347 - 446 °F	
Drying Temperature	82.2 °C	180 °F	
Dry Time	3 hour	3 hour	

Descriptive Properties	Value	Comments
Color	Black	
Form	Pellets	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China