

## ExxonMobil Santoprene® 271-73 Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Vulcanizate Elastomer (TPV)

### Material Notes:

A soft, colorable, specialty thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. It complies with FDA regulations for rubber articles intended for repeated use, as well as those in contact with non-fatty, non-oily foods as closures and sealing gaskets. This grade of Santoprene TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding, extrusion or blow molding. It is polyolefin based and completely recyclable. Key Features: This product, in principle, can be used in food contact applications in the USA (FDA). Migration or use limitations may apply. Complies with NSF Standard 51: Food Equipment Materials - Plastics, materials and components used in food equipment. UL listed: file #QMFZ2.E80017, Plastics - Component; file #QMFZ8.E80017, Plastics Certified For Canada - Component. Recommended for applications requiring excellent flex fatigue resistance. EU and China RoHS compliant. Applications: Consumer – FDA Seals and Closures, Packaging, Small Appliance and Soft Touch Grips. Seals and Gaskets. Soft Touch Grips. Uses: Filters, Flexible Grips, Food Containers, Gaskets, Kitchenware, Living Hinges, Non-specific Food Applications, Seals, Tubing, White Goods & Small Appliances. Availability: Africa & Middle East, Europe, North America, Asia Pacific, Latin America and South America. Information provided by ExxonMobil Chemical

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ExxonMobil-Santoprene-271-73-Thermoplastic-Elastomer.php](http://www.lookpolymers.com/polymer_ExxonMobil-Santoprene-271-73-Thermoplastic-Elastomer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.960 g/cc	0.960 g/cc	23°C; ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	78	78	2 mm, 15 sec; ISO 868
	85	85	Air at 302°F, 168 hr; ASTM D573
Tensile Strength at Break	8.7370 MPa	1267.2 psi	Air at 302°F, 168 hr; ASTM D573
	8.83 MPa	1280 psi	Across Flow; ASTM D412
Tensile Stress	3.60 MPa	522 psi	Across Flow; ASTM D412
	@Strain 100 %	@Strain 100 %	
Elongation at Break	475.3 %	475.3 %	Air at 302°F, 168 hr; ASTM D573
	490 %	490 %	Across Flow; ASTM D412
Tear Strength	27.0 kN/m	154 pli	73°F, Die C; ASTM D624
Compression Set	28 %	28 %	158°F, 22 hr; ASTM D395
	37 %	37 %	257°F, 70 hr; ASTM D395

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties	-60.0 °C Metric	-76.0 °F English	ASTM D746 Comments
--------------------	--------------------	---------------------	-----------------------

Processing Properties	Metric	English	Comments
Processing Temperature	175 - 230 °C	347 - 446 °F	
Rear Barrel Temperature	177 °C	350 °F	
Middle Barrel Temperature	182 °C	360 °F	
Front Barrel Temperature	182 °C	360 °F	
Nozzle Temperature	193 - 227 °C	380 - 440 °F	
Die Temperature	204 °C	400 °F	Extrusion
Melt Temperature	202 °C	395 °F	Extrusion
	199 - 232 °C	390 - 450 °F	
Mold Temperature	10.0 - 51.7 °C	50.0 - 125 °F	Processing
Drying Temperature	82.2 °C	180 °F	
Dry Time	3 hour	3 hour	
Moisture Content	0.080 %	0.080 %	
Back Pressure	0.345 - 0.689 MPa	50.0 - 100 psi	Processing
	5.00 - 20.0 MPa	725 - 2900 psi	Extrusion
Clamp Pressure	41.4 - 68.9 MPa	6000 - 10000 psi	
Vent Depth	0.00254 cm	0.00100 in	
Cushion	0.317 - 0.635 cm	0.125 - 0.250 in	
Screw Speed	100 - 200 rpm	100 - 200 rpm	

Descriptive Properties	Value	Comments
Color	Natural Color	
Form	Pellets	
Injection Rate	Fast	
Maximum Regrind %	20	
Screw Compression Ratio	2:1 - 2.5:1	
Screw L/D Ratio	16:1 - 20:1	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**