

## ExxonMobil Santoprene® 283-40MED Thermoplastic Elastomer (discontinued \*\*)

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Vulcanizate Elastomer (TPV)

### Material Notes:

A hard, colorable, specialty thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. USP Class VI Certificates of Compliance exist for representative samples of our medical grades. Prior to release, each medical grade lot undergoes a Cytotoxicity study using the ISO elution method and a Physico-Chemical - Elastomeric Closures test for heavy metals such as lead. This grade of Santoprene TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding, extrusion or blow molding. It is polyolefin based and completely recyclable. Information provided by Advanced Elastomer Systems

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ExxonMobil-Santoprene-283-40MED-Thermoplastic-Elastomer-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_ExxonMobil-Santoprene-283-40MED-Thermoplastic-Elastomer-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.940 g/cc	0.940 g/cc	23°C; ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	39	39	.12 in; ASTM D2240
Tensile Strength at Break	14.28 MPa	2071 psi	Air at 212°F, 168 hr; ASTM D573
	15.0 MPa	2180 psi	Across Flow; ASTM D412
Tensile Strength, Ultimate	8.48 MPa	1230 psi	Across Flow; ASTM D412
Elongation at Break	480.6 %	480.6 %	Air at 212°F, 168 hr; ASTM D573
	540 %	540 %	Across Flow; ASTM D412
Tear Strength	28.0 kN/m	160 pli	212°F, Die C; ASTM D624
	54.0 kN/m	308 pli	73°F, Die C; ASTM D624
Compression Set	43 %	43 %	73°F, 168 hr; ASTM D395
	60 %	60 %	212°F, 168 hr; ASTM D395

Processing Properties	Metric	English	Comments
Processing Temperature	175 - 230 °C	347 - 446 °F	

Descriptive Properties	Value	Comments
Color	Natural Color	
Form	Pellets	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**