

ExxonMobil Santoprene® 8191-60B500 Thermoplastic Vulcanizate (discontinued **)

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Vulcanizate Elastomer (TPV)

Material Notes:

Product Description: A soft, black, specialty thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. It is especially formulated to bond to PA 6, PA 6/6, PA 6 GF, PA 11, PA 12 and PA 6/12 substrates in applications where hard/soft combinations are required. This grade of Santoprene TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding or extrusion. It is polyolefin based and completely recyclable.**Key Features:**Designed for excellent adhesion to PA6, PA6/6, PA6GF, PA11, PA 12 and PA6/12 (cold insert or 2K [two-shot] molding).Broad processing window for injection molding.Recommended for applications requiring superior part surface appearance.EU and China RoHS compliant.Information provided by ExxonMobil Chemical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Santoprene-8191-60B500-Thermoplastic-Vulcanizate-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.980 g/cc	0.980 g/cc	ASTM D792 and ISO 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65	65	2 mm; ISO 868
	@Time 15.0 sec	@Time 0.00417 hour	
Tensile Strength at Break	2.80 MPa	406 psi	Across Flow; ASTM D412 and ISO 37
Tensile Stress	2.10 MPa	305 psi	Across Flow; ASTM D412 and ISO 37
	@Strain 100 %	@Strain 100 %	
Elongation at Break	200 %	200 %	Across Flow; ASTM D412 and ISO 37

Thermal Properties	Metric	English	Comments
Flammability, UL94	HB	HB	UL File Number - E80017
	@Thickness 1.10 mm	@Thickness 0.0433 in	
	HB	HB	
	@Thickness 3.00 mm	@Thickness 0.118 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China