

ExxonMobil Santoprene® 8211-65M300 Thermoplastic Elastomer (discontinued **)

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Vulcanizate Elastomer (TPV)

Material Notes:

A soft, colorable, UV resistant thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material is designed for automotive interior applications requiring low fogging and good appearance. This grade of Santoprene 8000 TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding. It is polyolefin based and completely recyclable. Non-hygroscopic product, requires little to no drying before processing. Neutral, easy coloring formulation. Excellent ozone resistance. Used in sealing applications. Recommended for applications requiring excellent flex fatigue resistance. Information provided by Advanced Elastomer Systems

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Santoprene-8211-65M300-Thermoplastic-Elastomer-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.920 g/cc	0.920 g/cc	23°C; ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	55 @Thickness 2.00 mm	55 @Thickness 0.0787 in	ISO 868
Tensile Strength at Break	4.69 MPa	680 psi	Across Flow; ASTM D412
Tensile Strength, Ultimate	2.07 MPa	300 psi	Across Flow; ASTM D412
Elongation at Break	420 %	420 %	Across Flow; ASTM D412

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-60.0 °C	-76.0 °F	ASTM D746

Processing Properties	Metric	English	Comments
Processing Temperature	175 - 230 °C	347 - 446 °F	

Descriptive Properties	Value	Comments
Color	Natural Color	
Form	Pellets	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China