

ExxonMobil SpectraSyn Plus™ 3.6 Advanced Polyalphaolefin (PAO) Fluid

Category : Fluid , Lubricant , Polyalphaolefin (PAO)

Material Notes:

Product Description: SpectraSyn Plus™ Advanced Polyalphaolefin (PAO) provide an optimal combination of volatility and low-temperature fluidity. SpectraSyn Plus™ Advanced products viscosity indices translate into improved flow at low temperatures and increased film thickness at high temperatures. SpectraSyn Plus™ Advanced PAO provide superior lubrication as the primary basestocks for synthetic lubricants used in passenger car engines, heavy-duty diesel engines, transmissions, and a variety of industrial applications. SpectraSyn Plus™ Advanced PAO can be use for upgrading mineral oil or Group III basestock for improved low temperature and volatility performance.

Appearance: Bright & Clear**Availability:** Africa & Middle East, Asia Pacific, Central America, Europe, North America and South

AmericaInformation provided by ExxonMobil

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-SpectraSyn-Plus-36-Advanced-Polyalphaolefin-PAO-Fluid.php

Physical Properties	Metric	English	Comments
Density	0.816 g/cc	0.0295 lb/in ³	ASTM D4052
	@Temperature 15.6 °C	@Temperature 60.1 °F	
Viscosity	1.14 cP	1.14 cP	High-Temp. High Shear; ASTM D5481
	2060 cP	2060 cP	
	@Temperature -40.0 °C	@Temperature -40.0 °F	Apparent Viscosity by Mini-Rotary Viscometer; ASTM D4684
Brookfield Viscosity	2117 cP	2117 cP	ASTM D2983
	@Temperature -40.0 °C	@Temperature -40.0 °F	
Viscosity Measurement	120	120	Index; ASTM D2270
Kinematic Viscosity	2000 cSt	2000 cSt	ASTM D445
	@Temperature -40.0 °C	@Temperature -40.0 °F	
Kinematic Viscosity at 40°C (104°F)	15.4 cSt	15.4 cSt	ASTM D445
Kinematic Viscosity at 100°C (212°F)	3.6 cSt	3.6 cSt	ASTM D445
Vapor Pressure	0.000267 bar	0.200 torr	ASTM D2879
	@Temperature 150 °C	@Temperature 302 °F	
Evaporation Loss	22.6 %	22.6 %	ASTM D972
	@Temperature 205 °C, Time 23400 sec	@Temperature 401 °F, Time 6.50 hour	

Thermal Properties	Metric	English	Comments
Pour Point	<= -65.0 °C	<= -85.0 °F	ASTM D5950/D97

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Optical Properties	Metric	English	Comments
--------------------	--------	---------	----------

Refractive Index	1.453	1.453	ASTM D1218
------------------	-------	-------	------------

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Dielectric Constant	2.09	2.09	ASTM D924
---------------------	------	------	-----------

Dielectric Breakdown	41500 V	41500 V	
----------------------	---------	---------	--

Chemical Properties	Metric	English	Comments
---------------------	--------	---------	----------

Acid Value	<= 0.050	<= 0.050	[mg KOH/g]; ASTM D974 (mod)
------------	----------	----------	-----------------------------

Descriptive Properties	Value	Comments
------------------------	-------	----------

Aniline Point	246.2°F	ASTM D611
---------------	---------	-----------

Cold Cranking Simulator	1050 cP	-31°F, ASTM D5293
-------------------------	---------	-------------------

	660 cP	-22°F, ASTM D5293
--	--------	-------------------

Color	<0.5	ASTM D1500
-------	------	------------

Composition	Water	<50 ppm, ASTM D6304 (mod)
-------------	-------	---------------------------

Density Correction Factor	0.000648 (g/cc)/°C	ASTM D1250
---------------------------	--------------------	------------

Fire point	478°F	COC, ASTM D92
------------	-------	---------------

Noack Volatility	<17%	ASTM D5800/DIN 51581
------------------	------	----------------------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China