

ExxonMobil SpectraSyn Ultra™ 1000 High VI Polyalphaolefin (PAO) Fluid

Category : Fluid , Lubricant , Polyalphaolefin (PAO)

Material Notes:

Product Description: SpectraSyn Ultra™ High VI Polyalphaolefin (PAO) have high viscosity indices, low pour points, low traction, good air release, and low foaming tendency. The extremely high viscosity indices translate into improved flow at low temperatures and increased elastohydrodynamic lubricant film thickness at high temperatures. SpectraSyn Ultra™ High VI PAO are frequently combines with other synthetic basestocks (e.g. SpectraSyn Ultra™ PAO, Exterex™ esters, and/or Synesstic™ alkylated naphthalene) to obtain optical viscometric properties. ExxonMobil's SpectraSyn Ultra™ High VI PAO are particularly suited for applications that require improved wear protection.

Appearance: Bright & Clear
Availability: Africa & Middle East, Asia Pacific, Central America, Europe, North America and South

AmericaInformation provided by ExxonMobil

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-SpectraSyn-Ultra-1000-High-VI-Polyalphaolefin-PAO-Fluid.php

Physical Properties	Metric	English	Comments
Density	0.855 g/cc	0.0309 lb/in ³	ASTM D4052
	@Temperature 15.6 °C	@Temperature 60.1 °F	
Brookfield Viscosity	170000 cP	170000 cP	ASTM D2983
	@Temperature 32.0 °C	@Temperature 89.6 °F	
Viscosity Measurement	1.94e+6 cP	1.94e+6 cP	ASTM D2983
	@Temperature -4.00 °C	@Temperature 24.8 °F	
Viscosity Measurement	307	307	Index; ASTM D2270
Kinematic Viscosity	340 cSt	340 cSt	ASTM D445
	@Temperature 140 °C	@Temperature 284 °F	
Kinematic Viscosity	100000 cSt	100000 cSt	ASTM D445
	@Temperature 0.000 °C	@Temperature 32.0 °F	
Kinematic Viscosity at 40°C (104°F)	10000 cSt	10000 cSt	ASTM D445
Kinematic Viscosity at 100°C (212°F)	1000 cSt	1000 cSt	ASTM D445
Evaporation Loss	0.50 %	0.50 %	ASTM D972
	@Temperature 150 °C, Time 79200 sec	@Temperature 302 °F, Time 22.0 hour	

Thermal Properties	Metric	English	Comments
Pour Point	-17.8 °C	0.000 °F	ASTM D5950/D97
Flash Point	>= 265 °C	>= 509 °F	COC; ASTM D92

Optical Properties	Metric	English	Comments
Refractive Index	1.471	1.471	ASTM D1218

Chemical Properties	Metric	English	Comments
Acid Value	<= 0.10	<= 0.10	[mg KOH/g]; ASTM D974 (mod)

Descriptive Properties	Value	Comments
Color	<0.5	ASTM D1500
Composition	Water	<50 ppm, ASTM D6304 (mod)
Density Correction Factor	0.000504 (g/cc)/°C	ASTM D1250
Kauri-Butanol Value	3.2	ASTM D1133
Noack Volatility	0.003	ASTM D5800/DIN 51581

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China