

Fainplast Compounds ARC 20 Rigid PVC, Atoxic for General Purpose

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Rigid Grade

Material Notes:

Bottles medium/high antishock

Order this product through the following link:

http://www.lookpolymers.com/polymer_Fainplast-Compounds-ARC-20-Rigid-PVC-Atoxic-for-General-Purpose.php

Physical Properties	Metric	English	Comments
Density	1.34 - 1.38 g/cc	0.0484 - 0.0499 lb/in ³	ISO R 1184

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	39.0 MPa	5660 psi	ISO R 527
Tensile Strength, Yield	42.0 MPa	6090 psi	ISO R527
Elongation at Break	150 %	150 %	ISO R 527
Izod Impact, Unnotched	5.80 - 6.20 J/cm @Temperature 23.0 °C	10.9 - 11.6 ft-lb/in @Temperature 73.4 °F	ISO R180

Thermal Properties	Metric	English	Comments
Vicat Softening Point	75.0 - 77.0 °C @Load 5.00 kg	167 - 171 °F @Load 11.0 lb	ISO R306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China