

## Fainplast Compounds CKL 173 Flexible PVC, Sheathing Lead Free

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

**Material Notes:**

General purpose - good flexibility

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Fainplast-Compounds-CKL-173-Flexible-PVC-Sheathing-Lead-Free.php](http://www.lookpolymers.com/polymer_Fainplast-Compounds-CKL-173-Flexible-PVC-Sheathing-Lead-Free.php)

Physical Properties	Metric	English	Comments
Density	1.39 - 1.43 g/cc	0.0502 - 0.0517 lb/in <sup>3</sup>	ISO R 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	78 - 82	78 - 82	ISO R 868
Tensile Strength at Break	>= 15.0 MPa	>= 2180 psi	ISO R 527
Elongation at Break	>= 300 %	>= 300 %	ISO R 527

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-35.0 °C	-31.0 °F	Cold Flex; ISO 458/2

Descriptive Properties	Value	Comments
Thermal Stability (minutes)	60	CEI 20-34/3-2

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China