

## Fainplast Compounds CKL 70 Flexible PVC, Sheathing Lead Free

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

**Material Notes:**

General purposes

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Fainplast-Compounds-CKL-70-Flexible-PVC-Sheathing-Lead-Free.php](http://www.lookpolymers.com/polymer_Fainplast-Compounds-CKL-70-Flexible-PVC-Sheathing-Lead-Free.php)

Physical Properties	Metric	English	Comments
Density	1.23 - 1.27 g/cc	0.0444 - 0.0459 lb/in <sup>3</sup>	ISO R 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	68 - 72	68 - 72	ISO R 868
Tensile Strength at Break	>= 13.0 MPa	>= 1890 psi	ISO R 527
Elongation at Break	>= 280 %	>= 280 %	ISO R 527

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-36.0 °C	-32.8 °F	Cold Flex; ISO 458/2

Descriptive Properties	Value	Comments
Thermal Stability (minutes)	50	CEI 20-34/3-2

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China