

Fainplast Compounds GS 38/T Flexible PVC, Injection Molding for Transparent Technical Items

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Molded

Material Notes:

Dolls

Order this product through the following link:

http://www.lookpolymers.com/polymer_Fainplast-Compounds-GS-38T-Flexible-PVC-Injection-Molding-for-Transparent-Technical-Items.php

Physical Properties	Metric	English	Comments
Density	1.10 - 1.14 g/cc	0.0397 - 0.0412 lb/in ³	ISO R 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	36 - 40	36 - 40	ISO R 868
Tensile Strength at Break	5.00 MPa	725 psi	ISO R 527
Elongation at Break	350 %	350 %	ISO R 527

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-60.0 °C	-76.0 °F	

Optical Properties	Metric	English	Comments
Transmission, Visible	90 %	90 %	transparent; thickness not quantified

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China