

## Fainplast Compounds GS 59/F Flexible PVC, Injection Molding for Footwear

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Molded

**Material Notes:**

Sandals

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Fainplast-Compounds-GS-59F-Flexible-PVC-Injection-Molding-for-Footwear.php](http://www.lookpolymers.com/polymer_Fainplast-Compounds-GS-59F-Flexible-PVC-Injection-Molding-for-Footwear.php)

Physical Properties	Metric	English	Comments
Density	1.16 - 1.20 g/cc	0.0419 - 0.0434 lb/in <sup>3</sup>	ISO R 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	57 - 61	57 - 61	ISO R 868
Tensile Strength at Break	8.00 MPa	1160 psi	ISO R 527
Elongation at Break	400 %	400 %	ISO R 527
Abrasion	175	175	[mm <sup>3</sup> ]; DIN 53516

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-40.0 °C	-40.0 °F	Cold Flex; ISO 458/2

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China