

## Fainplast Compounds GS 7430 Flexible PVC, Injection Molding for Footwear

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Molded

**Material Notes:**

Sandals

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Fainplast-Compounds-GS-7430-Flexible-PVC-Injection-Molding-for-Footwear.php](http://www.lookpolymers.com/polymer_Fainplast-Compounds-GS-7430-Flexible-PVC-Injection-Molding-for-Footwear.php)

Physical Properties	Metric	English	Comments
Density	1.33 - 1.37 g/cc	0.0480 - 0.0495 lb/in <sup>3</sup>	ISO R 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	72 - 76	72 - 76	ISO R 868
Tensile Strength at Break	15.0 MPa	2180 psi	ISO R 527
Elongation at Break	350 %	350 %	ISO R 527

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-25.0 °C	-13.0 °F	Cold Flex; ISO 458/2

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China