

Fainplast Compounds GS 89/T Flexible PVC, Injection Molding for Transparent Technical Items

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Molded

Material Notes:

Technical items

Order this product through the following link:

http://www.lookpolymers.com/polymer_Fainplast-Compounds-GS-89T-Flexible-PVC-Injection-Molding-for-Transparent-Technical-Items.php

| Physical Properties | Metric | English | Comments |
|---------------------|------------------|------------------------------------|------------|
| Density | 1.22 - 1.26 g/cc | 0.0441 - 0.0455 lb/in ³ | ISO R 1183 |

| Mechanical Properties | Metric | English | Comments |
|---------------------------|----------|----------|-----------|
| Hardness, Shore A | 88 - 92 | 88 - 92 | ISO R 868 |
| Tensile Strength at Break | 18.0 MPa | 2610 psi | ISO R 527 |
| Elongation at Break | 320 % | 320 % | ISO R 527 |

| Optical Properties | Metric | English | Comments |
|-----------------------|--------|---------|---------------------------------------|
| Transmission, Visible | 90 % | 90 % | transparent; thickness not quantified |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China