

## Fainplast Compounds GSK 78/3 Flexible PVC, Injection Molding, Lead Free

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Molded

**Material Notes:**

Plugs DOP free

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Fainplast-Compounds-GSK-783-Flexible-PVC-Injection-Molding-Lead-Free.php](http://www.lookpolymers.com/polymer_Fainplast-Compounds-GSK-783-Flexible-PVC-Injection-Molding-Lead-Free.php)

Physical Properties	Metric	English	Comments
Density	1.41 - 1.45 g/cc	0.0509 - 0.0524 lb/in <sup>3</sup>	ISO R 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	76 - 80	76 - 80	ISO R 868
Tensile Strength at Break	12.0 MPa	1740 psi	ISO R 527
Elongation at Break	200 %	200 %	ISO R 527

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China