

Fainplast Compounds HAX HF 22G Halogen Free PVC

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

Material Notes:

Sheathing; standard grade improved processing speed

Order this product through the following link:

http://www.lookpolymers.com/polymer_Fainplast-Compounds-HAX-HF-22G-Halogen-Free-PVC.php

Physical Properties	Metric	English	Comments
Density	1.48 - 1.52 g/cc	0.0535 - 0.0549 lb/in ³	IEC 60811
Melt Index of Compound	7.0 g/10 min @Load 21.6 kg, Temperature 150 °C	7.0 g/10 min @Load 47.6 lb, Temperature 302 °F	Fainplast

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	48 - 54	48 - 54	IEC 60811
Tensile Strength at Break	11.0 MPa	1600 psi	IEC 60811
Elongation at Break	170 %	170 %	IEC 60811

Thermal Properties	Metric	English	Comments
Oxygen Index	33 %	33 %	ISO 4589

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm @Temperature 20.0 °C	1.00e+15 ohm-cm @Temperature 68.0 °F	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China