

## Fainplast Compounds Hax™ HF 225F Flame Retardant Polyolefin Cable Compound

Category : Polymer , Thermoplastic , Polyolefin , Polyolefin, Wire/Cable Grade

### Material Notes:

Thermoplastic halogen free flame retardant compound based on polyolefins and mineral fillers  
Grade description: Sheathing, high flexibility  
Information provided by Fainplast Compounds

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Fainplast-Compounds-Hax-HF-225F-Flame-Retardant-Polyolefin-Cable-Compound.php](http://www.lookpolymers.com/polymer_Fainplast-Compounds-Hax-HF-225F-Flame-Retardant-Polyolefin-Cable-Compound.php)

Physical Properties	Metric	English	Comments
Density	1.48 - 1.52 g/cc	0.0535 - 0.0549 lb/in <sup>3</sup>	ISO 1183
Melt Flow	9.0 g/10 min @Load 21.6 kg, Temperature 150 °C	9.0 g/10 min @Load 47.6 lb, Temperature 302 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	40 - 46	40 - 46	ISO 868
Tensile Strength	11.0 MPa	1600 psi	ISO 527
Elongation at Break	200 %	200 %	ISO 527

Thermal Properties	Metric	English	Comments
Oxygen Index	36 %	36 %	ISO 4589

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257

Processing Properties	Metric	English	Comments
Processing Temperature	100 - 180 °C	212 - 356 °F	extruder
Shelf Life	3.00 Month @Temperature 30.0 °C	3.00 Month @Temperature 86.0 °F	Moisture absorption after extended storage

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China