

Fainplast Compounds PK 88/2-UV Flexible PVC, Lead Free

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Extruded

Material Notes:

Outdoor profiles anti-UV

Order this product through the following link:

http://www.lookpolymers.com/polymer_Fainplast-Compounds-PK-882-UV-Flexible-PVC-Lead-Free.php

Physical Properties	Metric	English	Comments
Density	1.46 - 1.50 g/cc	0.0527 - 0.0542 lb/in ³	ISO R 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	86 - 90	86 - 90	ISO R 868
Tensile Strength at Break	15.0 MPa	2180 psi	ISO R 527
Elongation at Break	240 %	240 %	ISO R 527

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-15.0 °C	5.00 °F	Cold Flex; ISO 458/2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China