

Fainplast Compounds PM 64/OP Flexible PVC, Lead Free

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Extruded

Material Notes:

Gaskets, Opaque surface

Order this product through the following link:

http://www.lookpolymers.com/polymer_Fainplast-Compounds-PM-64OP-Flexible-PVC-Lead-Free.php

| Physical Properties | Metric | English | Comments |
|---------------------|------------------|------------------------------------|------------|
| Density | 1.21 - 1.25 g/cc | 0.0437 - 0.0452 lb/in ³ | ISO R 1183 |

| Mechanical Properties | Metric | English | Comments |
|---------------------------|----------|----------|-----------|
| Hardness, Shore A | 62 - 66 | 62 - 66 | ISO R 868 |
| Tensile Strength at Break | 12.0 MPa | 1740 psi | ISO R 527 |
| Elongation at Break | 300 % | 300 % | ISO R 527 |

| Thermal Properties | Metric | English | Comments |
|-------------------------|----------|----------|----------------------|
| Brittleness Temperature | -34.0 °C | -29.2 °F | Cold Flex; ISO 458/2 |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China