

Fainplast Compounds PMS 75 Flexible PVC, Lead Free

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Extruded

Material Notes:

Gas pipes stabilized Ca-Zn

Order this product through the following link:

http://www.lookpolymers.com/polymer_Fainplast-Compounds-PMS-75-Flexible-PVC-Lead-Free.php

Physical Properties	Metric	English	Comments
Density	1.24 - 1.28 g/cc	0.0448 - 0.0462 lb/in ³	ISO R 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	73 - 77	73 - 77	ISO R 868
Tensile Strength at Break	16.0 MPa	2320 psi	ISO R 527
Elongation at Break	280 %	280 %	ISO R 527

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-20.0 °C	-4.00 °F	Cold Flex; ISO 458/2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China