

## Fainplast Compounds RE 130 Rigid PVC, Extrusion

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Extruded

**Material Notes:**

Pipes and profiles

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Fainplast-Compounds-RE-130-Rigid-PVC-Extrusion.php](http://www.lookpolymers.com/polymer_Fainplast-Compounds-RE-130-Rigid-PVC-Extrusion.php)

Physical Properties	Metric	English	Comments
Density	1.57 - 1.61 g/cc	0.0567 - 0.0582 lb/in <sup>3</sup>	ISO R 1184

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	33.0 MPa	4790 psi	ISO R 527
Tensile Strength, Yield	38.0 MPa	5510 psi	
Elongation at Break	80 %	80 %	ISO R 527
Izod Impact, Unnotched	0.500 - 0.900 J/cm @Temperature 23.0 °C	0.937 - 1.69 ft-lb/in @Temperature 73.4 °F	ISO R180

Thermal Properties	Metric	English	Comments
Vicat Softening Point	83.0 - 85.0 °C @Load 5.00 kg	181 - 185 °F @Load 11.0 lb	ISO R306

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China