

## Fainplast Compounds RE 265/D Rigid PVC, Extrusion

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Extruded

**Material Notes:**

Semi-rigid furniture border

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Fainplast-Compounds-RE-265D-Rigid-PVC-Extrusion.php](http://www.lookpolymers.com/polymer_Fainplast-Compounds-RE-265D-Rigid-PVC-Extrusion.php)

| Physical Properties | Metric           | English                            | Comments   |
|---------------------|------------------|------------------------------------|------------|
| Density             | 1.48 - 1.52 g/cc | 0.0535 - 0.0549 lb/in <sup>3</sup> | ISO R 1184 |

| Mechanical Properties     | Metric  | English                                       | Comments  |
|---------------------------|---|---|-----------|
| Tensile Strength at Break | 24.0 MPa                                      | 3480 psi                                      | ISO R 527 |
| Tensile Strength, Yield   | 28.0 MPa                                      | 4060 psi                                      | ISO R527  |
| Elongation at Break       | 150 %   | 150 %   | ISO R 527 |
| Izod Impact, Unnotched    | 0.800 - 1.20 J/cm<br>@Temperature 23.0<br>Â°C | 1.50 - 2.25 ft-lb/in<br>@Temperature 73.4 Â°F | ISO R180  |

| Thermal Properties    | Metric                           | English                        | Comments |
|-----------------------|----------------------------------|--------------------------------|----------|
| Vicat Softening Point | 56.0 - 58.0 Â°C<br>@Load 5.00 kg | 133 - 136 Â°F<br>@Load 11.0 lb | ISO R306 |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China