

Fainplast Compounds RKS 315/W Rigid PVC, Antishock Extrusion Lead Free

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Extruded

Material Notes:

Various profiles antishock

Order this product through the following link:

http://www.lookpolymers.com/polymer_Fainplast-Compounds-RKS-315W-Rigid-PVC-Antishock-Extrusion-Lead-Free.php

Physical Properties	Metric	English	Comments
Density	1.44 - 1.48 g/cc	0.0520 - 0.0535 lb/in ³	ISO R 1184

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	38.0 MPa	5510 psi	ISO R 527
Tensile Strength, Yield	42.0 MPa	6090 psi	ISO R527
Elongation at Break	120 %	120 %	ISO R 527
Izod Impact, Unnotched	5.80 - 6.20 J/cm @Temperature 23.0 Â°C	10.9 - 11.6 ft-lb/in @Temperature 73.4 Â°F	ISO R180

Thermal Properties	Metric	English	Comments
Vicat Softening Point	78.0 - 80.0 Â°C @Load 5.00 kg	172 - 176 Â°F @Load 11.0 lb	ISO R306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China