

## Ferro CF 7567 Low-Temperature Sealing

Category : Ceramic , Glass

**Material Notes:**

VITREOUS Typical Powder Form: TF Ferro's line of low-temperature sealing glasses are comprised of lead-borate (vitreous) and lead-zinc-borate crystallizing glasses formulated to meet specific thermal expansion requirements. Uses include hermetic and compression sealing of IC packages, plasma displays, CRTs, ferrites, fiber optics, as well as other ceramic, metal and glass substrate materials. Information provided by Ferro Corporation

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Ferro-CF-7567-Low-Temperature-Sealing.php](http://www.lookpolymers.com/polymer_Ferro-CF-7567-Low-Temperature-Sealing.php)

Physical Properties	Metric	English	Comments
Density	6.68 g/cc	0.241 lb/in <sup>3</sup>	
Particle Size	10 - 16 $\mu\text{m}$	10 - 16 $\mu\text{m}$	50% of particles
	$\leq 75 \mu\text{m}$	$\leq 75 \mu\text{m}$	

Mechanical Properties	Metric	English	Comments
Heat Seal Strength Initiation Temperature	420 $^{\circ}\text{C}$	788 $^{\circ}\text{F}$	15 min

Thermal Properties	Metric	English	Comments
CTE, linear	12.0 $\mu\text{m}/\text{m}\text{-}^{\circ}\text{C}$	6.67 $\mu\text{in}/\text{in}\text{-}^{\circ}\text{F}$	at Set Pt.
	11.3 $\mu\text{m}/\text{m}\text{-}^{\circ}\text{C}$	6.28 $\mu\text{in}/\text{in}\text{-}^{\circ}\text{F}$	
	@Temperature 260 $^{\circ}\text{C}$	@Temperature 500 $^{\circ}\text{F}$	
Softening Point	358 $^{\circ}\text{C}$	676 $^{\circ}\text{F}$	
Annealing Point	303 $^{\circ}\text{C}$	577 $^{\circ}\text{F}$	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China