

Fiberfil® FPI-15 BK Nylon 6, 15% Glass Reinforced, post industrial

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Information provided by FIBERFIL Engineered Plastics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Fiberfil-FPI-15-BK-Nylon-6-15-Glass-Reinforced-post-industrial.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	110 MPa	16000 psi	ASTM D638
Flexural Strength	171 MPa	24800 psi	ASTM D790
Flexural Modulus	4.90 GPa	711 ksi	Secant; ASTM D790
Izod Impact, Notched	0.603 J/cm @Thickness 3.17 mm	1.13 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	200 Â°C	392 Â°F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China