

## Fiberfil® J-69/30/E/M High performance polypropylene Homopolymer, 30% Glass Reinforced, Chemically coupled

Category : Polymer , Thermoplastic , Polypropylene (PP)

### Material Notes:

Information provided by FIBERFIL Engineered Plastics

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Fiberfil-J-6930EM-High-performance-polypropylene-Homopolymer-30-Glass-Reinforced-Chemically-coupled.php](http://www.lookpolymers.com/polymer_Fiberfil-J-6930EM-High-performance-polypropylene-Homopolymer-30-Glass-Reinforced-Chemically-coupled.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.13 g/cc	1.13 g/cc	ASTM D792
Water Absorption	0.030 %	0.030 %	24 hr; ASTM D570
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	ASTM D955
	@Thickness 3.17 mm	@Thickness 0.125 in	
	0.0040 cm/cm	0.0040 in/in	ASTM D955
	@Thickness 6.35 mm	@Thickness 0.250 in	
Melt Flow	13 g/10 min	13 g/10 min	230/2.16 (typical); ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	105 - 110	105 - 110	ASTM D785
Tensile Strength, Yield	100 MPa	14500 psi	ASTM D638
Elongation at Yield	2.0 %	2.0 %	ASTM D638
Tensile Modulus	6.89 GPa	1000 ksi	ASTM D638
Flexural Strength	124 MPa	18000 psi	ASTM D790
Flexural Modulus	6.21 GPa	900 ksi	Tangent; ASTM D790
Izod Impact, Notched	0.961 J/cm	1.80 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	160 Â°C	320 Â°F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	154 Â°C	310 Â°F	ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	204 - 221 Â°C	400 - 430 Â°F	
Middle Barrel Temperature	216 - 232 Â°C	420 - 450 Â°F	
Front Barrel Temperature	204 - 227 Â°C	400 - 440 Â°F	
Nozzle Temperature	204 - 221 Â°C	400 - 430 Â°F	
Melt Temperature	210 - 232 Â°C	410 - 450 Â°F	
Mold Temperature	37.8 - 65.6 Â°C	100 - 150 Â°F	
Back Pressure	0.172 - 0.345 MPa	25.0 - 50.0 psi	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China