

Fiberfil® M-2271 NAT Nylon 6, 33% Glass Reinforced, post industrial, natural

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Information provided by FIBERFIL Engineered Plastics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Fiberfil-M-2271-NAT-Nylon-6-33-Glass-Reinforced-post-industrial-natural.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.38 g/cc	1.38 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	145.0 MPa	21030 psi	ASTM D638
Flexural Strength	240.99 MPa	34953 psi	ASTM D790
Flexural Modulus	8.100 GPa	1175 ksi	Secant; ASTM D790
Izod Impact, Notched	1.20 J/cm @Thickness 3.17 mm	2.25 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	207 Â°C	405 Â°F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China