

Fiberfil® M-2494 BK Nylon 6, 30% FiberGlass Reinforced, post industrial grade

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Information provided by FIBERFIL Engineered Plastics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Fiberfil-M-2494-BK-Nylon-6-30-FiberGlass-Reinforced-post-industrial-grade.php

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	120 MPa	17400 psi	ASTM D638
Elongation at Yield	3.5 %	3.5 %	ASTM D638
Flexural Strength	190.0 MPa	27550 psi	ASTM D790
Flexural Modulus	6.998 GPa	1015 ksi	Secant; ASTM D790
Izod Impact, Notched	0.998 J/cm @Thickness 3.17 mm	1.87 ft-lb/in @Thickness 0.125 in	ASTM D256

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China