

Fiberfil® PP-60/VO/NH Polypropylene Homopolymer, Flame Retardant, non-halogenated, UL94 V0

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Information provided by FIBERFIL Engineered Plastics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Fiberfil-PP-60VONH-Polypropylene-Homopolymer-Flame-Retardant-non-halogenated-UL94-V0.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.07 g/cc	1.07 g/cc	ASTM D792
Water Absorption	0.020 %	0.020 %	24 hr; ASTM D570
Linear Mold Shrinkage	0.013 - 0.017 cm/cm	0.013 - 0.017 in/in	ASTM D955
	@Thickness 3.17 mm	@Thickness 0.125 in	
	0.018 - 0.022 cm/cm	0.018 - 0.022 in/in	ASTM D955
	@Thickness 6.35 mm	@Thickness 0.250 in	
Melt Flow	15 - 20 g/10 min	15 - 20 g/10 min	230/2.16 (typical); ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	90 - 95	90 - 95	ASTM D785
Tensile Strength, Yield	20.7 MPa	3000 psi	ASTM D638
Elongation at Yield	10 %	10 %	ASTM D638
Tensile Modulus	2.31 GPa	335 ksi	ASTM D638
Flexural Strength	33.1 MPa	4800 psi	ASTM D790
Flexural Modulus	2.24 GPa	325 ksi	Tangent; ASTM D790
Izod Impact, Notched	0.267 J/cm	0.500 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	85.0 Å°C	185 Å°F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	73.9 Å°C	165 Å°F	ASTM D648
	V-0	V-0	

Flammability UL 94			
Thermal Properties	Metric @ Thickness 1.47 mm	English @ Thickness 0.0579 in	Comments
Processing Properties	Metric	English	Comments
Rear Barrel Temperature	182 - 199 Â°C	360 - 390 Â°F	
Middle Barrel Temperature	193 - 210 Â°C	380 - 410 Â°F	
Front Barrel Temperature	188 - 204 Â°C	370 - 400 Â°F	
Nozzle Temperature	182 - 193 Â°C	360 - 380 Â°F	
Melt Temperature	193 - 216 Â°C	380 - 420 Â°F	
Mold Temperature	32.2 - 71.1 Â°C	90.0 - 160 Â°F	
Drying Temperature	76.7 Â°C	170 Â°F	Drying not normally required
Dry Time	2 hour	2 hour	Drying not normally required
Moisture Content	<= 0.20 %	<= 0.20 %	recommended for molding
Back Pressure	0.000 - 0.689 MPa	0.000 - 100 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China