

## Fiberfil® PP-68/TC/20 Polypropylene Copolymer, 20% Talc

Category : Polymer , Thermoplastic , Polypropylene (PP)

### Material Notes:

Information provided by FIBERFIL Engineered Plastics

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Fiberfil-PP-68TC20-Polypropylene-Copolymer-20-Talc.php](http://www.lookpolymers.com/polymer_Fiberfil-PP-68TC20-Polypropylene-Copolymer-20-Talc.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.06 g/cc	1.06 g/cc	ASTM D792
Water Absorption	0.020 %	0.020 %	24 hr; ASTM D570
Linear Mold Shrinkage	0.010 cm/cm	0.010 in/in	ASTM D955
	@Thickness 3.17 mm	@Thickness 0.125 in	
	0.012 cm/cm	0.012 in/in	ASTM D955
	@Thickness 6.35 mm	@Thickness 0.250 in	
Melt Flow	7.0 g/10 min	7.0 g/10 min	230/2.16 (typical); ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	80 - 85	80 - 85	ASTM D785
Tensile Strength, Yield	27.6 MPa	4000 psi	ASTM D638
Elongation at Yield	30 %	30 %	ASTM D638
Tensile Modulus	2.48 GPa	360 ksi	ASTM D638
Flexural Strength	40.0 MPa	5800 psi	ASTM D790
Flexural Modulus	2.34 GPa	340 ksi	Tangent; ASTM D790
Izod Impact, Notched	0.801 J/cm	1.50 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	82.2 Å°C	180 Å°F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	76.7 Å°C	170 Å°F	ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	199 - 210 Å°C	390 - 410 Å°F	

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	204 - 227 Â°C	400 - 440 Â°F	
Front Barrel Temperature	182 - 199 Â°C	360 - 390 Â°F	
Nozzle Temperature	182 - 193 Â°C	360 - 380 Â°F	
Melt Temperature	199 - 232 Â°C	390 - 450 Â°F	
Mold Temperature	32.2 - 71.1 Â°C	90.0 - 160 Â°F	
Drying Temperature	76.7 Â°C	170 Â°F	Drying not normally required
Dry Time	2 hour	2 hour	Drying not normally required
Moisture Content	<= 0.20 %	<= 0.20 %	recommended for molding
Back Pressure	0.000 - 0.689 MPa	0.000 - 100 psi	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China