

Fibre Glast EZ Poxy EZ10 / EZ83 Epoxy (discontinued **)

Category : Polymer , Thermoset , Epoxy , Epoxy, Molded, Glass Fiber Filler

Material Notes:

Information provided by Fibre Glast Developments Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Fibre-Glast-EZ-Poxy-EZ10-EZ83-Epoxy-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in ³	
Viscosity	750 cP	750 cP	ASTM D2293

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	88	88	Cured; ASTM D2240
Tensile Strength at Break	281.8 MPa	40870 psi	Property derived with 10 Ply Laminate, hand Lay-up, Style 181 Glass Fabric, 55% Glass Content.; ASTM D638
Elongation at Break	1.97 %	1.97 %	Property derived with 10 Ply Laminate, hand Lay-up, Style 181 Glass Fabric, 55% Glass Content.; ASTM D638
Tensile Modulus	14.7 GPa	2130 ksi	Property derived with 10 Ply Laminate, hand Lay-up, Style 181 Glass Fabric, 55% Glass Content.
Flexural Strength	308.98 MPa	44814 psi	Property derived with 10 Ply Laminate, hand Lay-up, Style 181 Glass Fabric, 55% Glass Content.; ASTM D790
Flexural Modulus	19.5 GPa	2830 ksi	Property derived with 10 Ply Laminate, hand Lay-up, Style 181 Glass Fabric, 55% Glass Content.; ASTM D790

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	64.4 °C	148 °F	

Processing Properties	Metric	English	Comments
Pot Life	120 min @Temperature 25.0 °C	120 min @Temperature 77.0 °F	4 fl. Oz.; ASTM D2471

Descriptive Properties	Value	Comments
------------------------	-------	----------

Mix Ratio Descriptive Properties	100:44 Value	Resin:Hardener by Weight Comments
	2.13:1	Resin:Hardener by Volume

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China