

## Firestone C212-15C Nylon 6, Heat Stabilized

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Heat Stabilized

### Material Notes:

Off white color. Heat stabilized, Modified, and Lubricated. Chip size is 2 x 3.5 mm. Information provided by Firestone

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Firestone-C212-15C-Nylon-6-Heat-Stabilized.php](http://www.lookpolymers.com/polymer_Firestone-C212-15C-Nylon-6-Heat-Stabilized.php)

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in <sup>3</sup>	ASTM D792
Viscosity Measurement	3.2	3.2	Relative Viscosity; Sulfuric Acid
	82	82	Relative Viscosity; Formic Acid

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	79.2 MPa	11500 psi	ASTM D638
Elongation at Break	300 %	300 %	ASTM D412
Flexural Yield Strength	97.0 MPa	14100 psi	ASTM D790
Flexural Modulus	2.59 GPa	376 ksi	ASTM D790
Izod Impact, Notched	0.480 J/cm	0.899 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	220 Â°C	428 Â°F	
Deflection Temperature at 0.46 MPa (66 psi)	180 Â°C	356 Â°F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	65.0 Â°C	149 Â°F	ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	238 - 249 Â°C	460 - 480 Â°F	
Middle Barrel Temperature	238 - 249 Â°C	460 - 480 Â°F	
Front Barrel Temperature	243 - 260 Â°C	470 - 500 Â°F	
Nozzle Temperature	249 - 260 Â°C	480 - 500 Â°F	
Melt Temperature	249 - 260 Â°C	480 - 500 Â°F	
Mold Temperature	48.9 - 82.2 Â°C	120 - 180 Â°F	

Processing Properties	Metric	English	Comments
Dry Time	4 hour	4 hour	
Moisture Content	<= 0.080 %	<= 0.080 %	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China