

## Formosa Plastics Formolene® 4101N Staple Fiber and Injection Molding Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Fiber Grade

### Material Notes:

Homopolymer Applications: Staple Fiber and General Purpose Injection Molding Formolene 4101N is a medium viscosity, highly isotactic polypropylene homopolymer designed for Staple Fiber and general purpose injection molding applications. It contains a unique combination of stabilizers which give it process stability and end use performance. Meets all requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles intended for direct food contact. Specimens were injection molded according to the conditions specified in ASTM D4101. Information provided by Formosa Plastics Corporation, USA.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Formosa-Plastics-Formolene-4101N-Staple-Fiber-and-Injection-Molding-Polypropylene.php](http://www.lookpolymers.com/polymer_Formosa-Plastics-Formolene-4101N-Staple-Fiber-and-Injection-Molding-Polypropylene.php)

Physical Properties	Metric	English	Comments
Density	0.904 g/cc	0.0327 lb/in <sup>3</sup>	ASTM D1505
Melt Flow	12 g/10 min @Temperature 230 °C	12 g/10 min @Temperature 446 °F	1<sub>2</sub>; ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	112	112	ASTM D785
Tensile Strength, Yield	38.6 MPa	5600 psi	2" (50mm) per min.; ASTM D638
Elongation at Yield	8.5 %	8.5 %	2" (50mm) per min.; ASTM D638
Flexural Modulus	1.72 GPa	250 ksi	1.3mm per min, 1% secant; ASTM D790
Izod Impact, Notched	0.214 J/cm	0.400 ft-lb/in	ASTM D256
Impact	0.80	0.80	ft-lb/in Notched Charpy @23°C/73°F; ASTM D256

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China