

Formosa Plastics Formolene® 6550A Thin Walled Injection Molding **Polypropylene**

Category: Polymer, Thermoplastic, Polypropylene (PP), Polypropylene, Molded

Material Notes:

Impact CopolymerApplications: Housewares, containers and other rigid packaging. Formolene 6550A (DEVELOPMENTAL) is a medium impact, high flow, controlled rheology copolymer of polypropylene designed for such applications as housewares, containers, and other rigid packaging. It is characterized by its easy mold flow, excellent physical property balance and finished product dimensional stability. It contains a unique combination of stabilizers which give it excellent processing and usage performance. Specimens were injection molded according to the conditions specified in ASTM D4101.Information provided by Formosa Plastics Corporation, USA.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Formosa-Plastics-Formolene-6550A-Thin-Walled-Injection-Molding-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in³	ASTM D1505
Melt Flow	50 g/10 min	50 g/10 min	I ₂ ; ASTM D1238
	@Temperature 230 °C	@Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	89	89	ASTM D785
Tensile Strength, Yield	20.7 MPa	3000 psi	2" (50mm) per min.; ASTM D638
Elongation at Yield	5.0 %	5.0 %	2" (50mm) per min.; ASTM D638
Flexural Modulus	1.00 GPa	145 ksi	1.3mm per min, 1% secant; ASTM D790
Izod Impact, Notched	0.908 J/cm	1.70 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	93.0 °C	199 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058 Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China