

Formosa Plastics Formolene® L42009F Film (Butene Grade) LLDPE

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE)/Butene, Film

Material Notes:

Extra High Molecular Weight Hexene Copolymer Formolene® L42009F is a general-purpose film grade linear low density made using gas-phase technology. The resin exhibits excellent toughness and strength when drawn down to thin gauges. Formolene® L42009F meets all requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles intended for direct food contact. Applications: Blending Resin, Industrial Liners, Industrial Packaging, Garment Bags and Co-Extrusion Information provided by Formosa Plastics Corporation, USA

Order this product through the following link:

http://www.lookpolymers.com/polymer_Formosa-Plastics-Formolene-L42009F-Film-Butene-Grade-LLDPE.php

Physical Properties	Metric	English	Comments
Density	0.919 g/cc	0.0332 lb/in ³	ASTM D1505
Thickness	25.0 microns	0.984 mil	
Melt Flow	0.95 g/10 min @Load 2.16 kg, Temperature 190 °C	0.95 g/10 min @Load 4.76 lb, Temperature 374 °F	Condition E; ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	700 %	700 %	ASTM D882
Film Elongation at Break, TD	815 %	815 %	ASTM D882
Elmendorf Tear Strength MD	160 g	160 g	ASTM D1922
Elmendorf Tear Strength TD	400 g	400 g	ASTM D1922
Dart Drop Test	135 g	0.298 lb	ASTM D1709
Film Tensile Strength at Break, MD	35.2 MPa	5100 psi	ASTM D882
Film Tensile Strength at Break, TD	22.24 MPa	3225 psi	ASTM D882

Optical Properties	Metric	English	Comments
Haze	27 %	27 %	ASTM D1003
Gloss	36 %	36 %	45°C; ASTM D523

Processing Properties	Metric	English	Comments
Blow-up Ratio (BUR)	2.5	2.5	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China