

Formosa Plastics Formolene® L64220UT1 Rotational Molding LLDPE (discontinued **)

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Rotational Molding Grade

Material Notes:

Hexene Copolymer Applications: Large tanks, material handling equipment and industrial rotational molding applications. Formolene L64220U is fully heat and UV stabilized. Meets all requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles intended for direct food contact. Information provided by Formosa Plastics Corporation, USA.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Formosa-Plastics-Formolene-L64220UT1-Rotational-Molding-LLDPE-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.942 g/cc	0.0340 lb/in ³	ASTM D1505
Environmental Stress Crack Resistance	>= 500 hour	>= 500 hour	(10% Igepal), F₅₀; ASTM D1693
	>= 1000 hour	>= 1000 hour	(100% Igepal), F₅₀; ASTM D1693
Melt Flow	2.0 g/10 min	2.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	21.4 MPa	3100 psi	2" (50mm) per min.; ASTM D638
Elongation at Yield	11.8 %	11.8 %	2" (50mm) per min.; ASTM D638
Flexural Modulus	0.827 GPa	120 ksi	1.3mm per min; ASTM D790
Dynatup @ -30°C	81.3 J	60.0 ft-lb	ARM Std. Low Temp Impact; ARM Std.
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	56.0 °C	133 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China