## Freudenberg Simrit Simriz® 486 Universal FFKT Perfluoroelastomer Compound

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

## **Material Notes:**

Perfluoro elastomers â e or FFKM for short â e have an ideal combination of characteristics, with their excellent chemical resistance, high level of temperature resistance, and high levels of elasticity. Simriz® perfluoro elastomers close the material gap between inelastic PTFE and elastomers, which have poor temperature and chemical resistance properties. With a fluoridation level of 72%, FFKM elastomers have a level of resistance close to that of pure PTFE at 76%. At the same time, FFKM materials are so elastic that they are excellently suited to both static and dynamic seals. Simrit offers ISC O-Rings which are specifically optimised with respect to flexibility at low temperatures, resistance to high temperatures, hardness, tensile strength, elongation, compression set, or color.Information provided by Freudenburg-NOK.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Freudenberg-Simrit-Simriz-486-Universal-FFKT-Perfluoroelastomer-Compound.php

| Mechanical Properties      | Metric              | English             | Comments |  |
|----------------------------|---------------------|---------------------|----------|--|
| Hardness, Shore A          | 75                  | 75                  |          |  |
| Tensile Strength, Ultimate | 18.0 MPa            | 2610 psi            |          |  |
| Elongation at Break        | 190 %               | 190 %               |          |  |
| Compression Set            | 25 %                | 25 %                | 70 hr    |  |
|                            | @Temperature 200 °C | @Temperature 392 °F | 1011     |  |

| Thermal Properties               | Metric   | English | Comments |
|----------------------------------|----------|---------|----------|
| Maximum Service Temperature, Air | 260 °C   | 500 °F  |          |
| Minimum Service Temperature, Air | -15.0 °C | 5.00 °F |          |

| Descriptive Properties | Value | Comments    |
|------------------------|-------|-------------|
| Color                  | White |             |
| Water Resistance       | 5.9   | 70 h; 200°C |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers



Address : United North Road 215, Fengxian District, Shanghai City, China