

## Freudenberg Simrit V123 Standard Fluoroelastomer

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Excellent resistance to petroleum products and solvents. Very good high-temperature performance. Fluorocarbon elastomers make up the most widely used seals in the semiconductor industry. Avoid polar solvents, amines, anhydrous ammonia, skydrol, hydrazine and hot acids.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Freudenberg-Simrit-V123-Standard-Fluoroelastomer.php](http://www.lookpolymers.com/polymer_Freudenberg-Simrit-V123-Standard-Fluoroelastomer.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	73	73	
Tensile Strength, Ultimate	17.6 MPa	2550 psi	
Elongation at Break	140 %	140 %	
Compression Set	15 % @Temperature 200 Â°C, Time 252000 sec	15 % @Temperature 392 Â°F, Time 70.0 hour	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	200 Â°C	392 Â°F	
Minimum Service Temperature, Air	-35.0 Â°C	-31.0 Â°F	

Descriptive Properties	Value	Comments
Color	Black	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China