

Fujipoly Industries Sarcon[®] 30T Thin-Film TR

Category : Polymer , Thermoset , Silicone

Material Notes:

Sarcon TR is Fujipolys originally developed High Heat Conductive Silicone Rubber. Fine, high heat conductive ceramic particles are mixed with insulative silicone rubber. Sarcon GTR is a composite of Heat Conductive Silicone Rubber and fiberglass. Information provided by Fujipoly Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_Fujipoly-Industries-Sarcon-30T-Thin-Film-TR.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	73	73	60 [°] C for 500 hrs; ASTM D2240
	75	75	ASTM D2240
	83	83	150 [°] C for 1,000 hrs; ASTM D2240
	90	90	200 [°] C for 1,000 hrs; ASTM D2240
Tensile Strength, Yield	5.66 MPa	821 psi	
	6.00 MPa	870 psi	150 [°] C for 1,000 hrs
	7.00 MPa	1020 psi	200 [°] C for 1,000 hrs
Elongation at Yield	30 %	30 %	200 [°] C for 1,000 hrs
	50 %	50 %	150 [°] C for 1,000 hrs
	100 %	100 %	
Tear Strength	0.300 kN/m	1.71 pli	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	182 [°] C	360 [°] F	
Minimum Service Temperature, Air	-60.0 [°] C	-76.0 [°] F	
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Volume Resistivity	6.10e+13 ohm-cm	6.10e+13 ohm-cm	60 [°] C for 500 hrs
	1.00e+15 ohm-cm	1.00e+15 ohm-cm	
	5.60e+15 ohm-cm	5.60e+15 ohm-cm	150 [°] C for 1,000 hrs

Electrical Properties	7.20e+15 ohm-cm Metric	7.20e+15 ohm-cm English	200Å°C for 1,000 hrs Comments
Dielectric Constant	4.2	4.2	After 1000 hrs at 150Å°C
	@Frequency 50 Hz	@Frequency 50 Hz	
	4.2	4.2	After 1000 hrs at 200Å°C
	@Frequency 50 Hz	@Frequency 50 Hz	
	4.2	4.2	After 1000 hrs at 200Å°C
	@Frequency 1000 Hz	@Frequency 1000 Hz	
	4.2	4.2	After 1000 hrs at 200Å°C
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	4.3	4.3	After 1000 hrs at 150Å°C
@Frequency 1e+6 Hz	@Frequency 1e+6 Hz		
4.3	4.3	After 1000 hrs at 150Å°C	
@Frequency 1000 Hz	@Frequency 1000 Hz		
4.5	4.5	After 500 hrs at 60Å°C	
@Frequency 1e+6 Hz	@Frequency 1e+6 Hz		
4.6	4.6	After 500 hrs at 60Å°C	
@Frequency 1000 Hz	@Frequency 1000 Hz		
4.8	4.8	After 500 hrs at 60Å°C	
@Frequency 50 Hz	@Frequency 50 Hz		
Dielectric Strength	6.00 kV/mm	152 kV/in	60Å°C for 500 hrs
	8.00 kV/mm	203 kV/in	AC 60 Hz; 200Å°C for 1,000 hrs
	8.40 kV/mm	213 kV/in	AC 60 Hz; 150Å°C for 1,000 hrs
	10.0 kV/mm	254 kV/in	AC 60 Hz
Dielectric Breakdown	7000 V	7000 V	Withstand Voltage [V/min]; AC 60 Hz
Dissipation Factor	0.0020	0.0020	After 1000 hrs at 150Å°C
	@Frequency 1000 Hz	@Frequency 1000 Hz	
	0.0020	0.0020	After 1000 hrs at 200Å°C
@Frequency 1000 Hz	@Frequency 1000 Hz		
	0.0020	0.0020	
	@Frequency 1000 Hz	@Frequency 1000 Hz	

Electrical Properties	0.0030 Metric	0.0030 English	Comments
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	0.0030	0.0030	After 1000 hrs at 200Â°C
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	0.0030	0.0030	After 1000 hrs at 150Â°C
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	0.0040	0.0040	After 1000 hrs at 200Â°C
	@Frequency 50 Hz	@Frequency 50 Hz	
	0.0040	0.0040	After 1000 hrs at 150Â°C
	@Frequency 50 Hz	@Frequency 50 Hz	
	0.0040	0.0040	
	@Frequency 50 Hz	@Frequency 50 Hz	
	0.0060	0.0060	After 500 hrs at 60Â°C
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	0.014	0.014	After 500 hrs at 60Â°C
	@Frequency 1000 Hz	@Frequency 1000 Hz	
	0.030	0.030	After 500 hrs at 60Â°C
	@Frequency 50 Hz	@Frequency 50 Hz	

Descriptive Properties	Value	Comments
Color	Gray-Green	
Thermal Impedance	0.62Â°C/W	FTM P-3010; ASTM D5470

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China