

## Fujipoly Industries Sarcon<sup>®</sup> GR-HFd Gap Filler Pad

Category : Polymer , Thermoset , Silicone

### Material Notes:

Sarcon GR-d is a highly conformable, thermally conductive material in areas where space between surfaces is uneven and surface textures vary. GR-HFd has a hardened top surface and mesh embedded overall. Information provided by Fujipoly Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Fujipoly-Industries-Sarcon-GR-HFd-Gap-Filler-Pad.php](http://www.lookpolymers.com/polymer_Fujipoly-Industries-Sarcon-GR-HFd-Gap-Filler-Pad.php)

Physical Properties	Metric	English	Comments
Specific Gravity	2.60 g/cc	2.60 g/cc	60 <sup>°</sup> C for 1,000 hrs with 90% RH; JIS-K-6220
	2.60 g/cc	2.60 g/cc	150 <sup>°</sup> C for 1,000 hrs; JIS-K-6220
	2.60 g/cc	2.60 g/cc	JIS-K-6220; ASTM D-792
	2.60 g/cc	2.60 g/cc	70 <sup>°</sup> C for 1,000 hrs; JIS-K-6220

Mechanical Properties	Metric	English	Comments
Hardness, Shore C	20	20	60 <sup>°</sup> C for 1,000 hrs with 90% RH; SRIS0101
	22	22	70 <sup>°</sup> C for 1,000 hrs; SRIS0101
	29	29	150 <sup>°</sup> C for 1,000 hrs; SRIS0101
Hardness, Shore OO	49	49	SRIS0101; ASTM D-2240
Tensile Strength, Yield	0.500 MPa	72.5 psi	150 <sup>°</sup> C for 1,000 hrs; JIS-K-6251(#2)
	0.700 MPa	102 psi	JIS-K-6251(#2)/ASTM D-412
	0.900 MPa	131 psi	60 <sup>°</sup> C for 1,000 hrs with 90% RH; JIS-K-6251(#2)
	1.50 MPa	218 psi	70 <sup>°</sup> C for 1,000 hrs; JIS-K-6251(#2)
Elongation at Yield	50 %	50 %	150 <sup>°</sup> C for 1,000 hrs; JIS-K-6251(#2)
	50 %	50 %	60 <sup>°</sup> C for 1,000 hrs with 90% RH; JIS-K-6251(#2)
	50 %	50 %	70 <sup>°</sup> C for 1,000 hrs; JIS-K-6251(#2)
	60 %	60 %	JIS-K-6251(#2)/ASTM D-412
Tear Strength	1.00 kN/m	5.71 pli	150 <sup>°</sup> C for 1,000 hrs; JIS-K-6252 (Angle)
	1.00 kN/m	5.71 pli	70 <sup>°</sup> C for 1,000 hrs; JIS-K-6252 (Angle)

Mechanical Properties	Metric	English	Comments (Angle)/ASTM D-624
	3.00 kN/m	17.1 pli	60°C for 1,000 hrs with 90% RH; JIS-K-6252 (Angle)

Thermal Properties	Metric	English	Comments
Thermal Conductivity	1.50 W/m-K	10.4 BTU-in/hr-ft <sup>2</sup> - °F	JIS-R-2618; ASTM D2326
	1.50 W/m-K	10.4 BTU-in/hr-ft <sup>2</sup> - °F	60°C for 1,000 hrs with 90% RH; JIS-R-2618
	1.50 W/m-K	10.4 BTU-in/hr-ft <sup>2</sup> - °F	70°C for 1,000 hrs; JIS-R-2618
Maximum Service Temperature, Air	200 °C	392 °F	
Minimum Service Temperature, Air	-60.0 °C	-76.0 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	8.00e+13 ohm-cm	8.00e+13 ohm-cm	60°C for 1,000 hrs with 90% RH; JIS-K-6249
	1.00e+14 ohm-cm	1.00e+14 ohm-cm	JIS-K-6249/ASTM D257
	6.80e+14 ohm-cm	6.80e+14 ohm-cm	150°C for 1,000 hrs; JIS-K-6249
	9.30e+14 ohm-cm	9.30e+14 ohm-cm	70°C for 1,000 hrs; JIS-K-6249
Dielectric Strength	10.0 kV/mm	254 kV/in	JIS-K-6249; ASTM D-149
	12.0 kV/mm	305 kV/in	70°C for 1,000 hrs; JIS-K-6249
	13.0 kV/mm	330 kV/in	60°C for 1,000 hrs with 90% RH; JIS-K-6249
	14.0 kV/mm	356 kV/in	150°C for 1,000 hrs; JIS-K-6249
Dielectric Breakdown	8000 V	8000 V	Withstand Voltage [V/min]; JIS-K-6249; ASTM D-149

Descriptive Properties	Value	Comments
Color	Dark Grey	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China